

# Outershield® MC715-H

## CLASSIFICATION

AWS A5.18	E70C-6M H4	A-Nr	1
EN ISO 17632-A	T 46 4 M M 2 H5	F-Nr	6
		9606 FM	1

## GENERAL DESCRIPTION

Metal cored gas shielded wire for all positions  
 Few silicates and virtually no spatter, fast travel speed, excellent wire feeding  
 Excellent arc characteristics give outstanding operator appeal  
 Excellent mechanical properties (CNV >47J at -40°C)  
 Superior product consistency with optimal alloy control  
 Depending on application good alternative for basic flux cored wires

## WELDING POSITIONS (ISO/ASME)



## CURRENT TYPE / SHIELDING GAS (ISO 14175)

DC +  
 M21 : Mixed gas Ar+ (>15-25%) CO<sub>2</sub>  
 Flow rate : 15-25 l/min

## APPROVALS

Shielding gas	BV	DB	DNV	GL	RINA
M21	SA3,3YMHH	+	IV Y40H5	4Y40H5S	4YSH5

## CHEMICAL COMPOSITION (W%), TYPICAL, ALL WELD METAL

Shielding gas	C	Mn	Si	P	S	HDM
M21	0.04	1.5	0.4	0.012	0.020	3 ml/100 g

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)		
						-30°C	-40°C	-50°C
Required: AWS A5.18 EN ISO 17632-A			min. 400 min. 460	min. 480 530-680	min. 22 min. 20		min. 47	
Typical values	M21	AW	480	580	27	120	110	80
	M21	SR	430	485	30		120	90

SR : 2h/640°C

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.0	1.2	1.4	1.6
5 kg plastic spool S200	X	X		
15 kg spool B300	X	X	X	X
200 kg Accutrak® Drum	X	X	X	X

Outershield® MC715-H: rev. C-EN28-12/05/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
 Fumes: Safety Data Sheets (SDS) are available on our website.

# Outershield<sup>®</sup> MC715-H

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades/Standard	Type
<b>General structural steels</b>	
EN 10025 part 2	S185, S235, S275, S355
<b>Ship plates</b>	
ASTM A131	Grade A, B, D, AH32 to EH40
<b>Cast steels</b>	
EN 10213-2	G P 240R
<b>Pipe material</b>	
EN 10208-1	L210, L240, L290, L360
EN 10208-2	L240NB, L290NB, L360NB, L360QB, L240MB,
L290MB, L360MB, L415MB, L415NB, L445	
API 5LX	X42, X46, X52, X60, X65
EN 10216-1/	P235T1, P235T2, P275T1
EN 10217-1	P275T2, P355N
<b>Boiler &amp; pressure vessel steels</b>	
EN 10028-2	P235GH, P265GH, P295GH, P355GH
<b>Fine grained steels</b>	
EN 10025 part 3	S275N, S275NL, S355N, S355NL, S420N, S420NL, S460N, S460NL
EN 10025 part 4	S275M, S275ML, S355M, S355ML, S420M, S420ML, S460M, S460ML

## CALCULATION DATA

Diameter (mm)	Arc mode	Electrical stick-out (mm)	Wire Feed Speed (cm/min)	Current (A)	Arc Voltage (V)	Deposition rate (kg/h)	kg wire/kg weldmetal
1.2	Short arc	15	230	100	15	1.1	1.10
			320	120	16	1.4	1.10
			400	150	17	1.9	1.10
1.2	Spray arc	20	635	180	28-30	2.7	1.10
			940	275	31-34	4.8	1.10
			1420	340	35-38	6.8	1.10
1.4	Short arc	15	205	105	14.5	1.2	1.10
			255	125	15.0	1.5	1.10
			280	135	15.5	1.6	1.10
1.4	Spray arc	20	445	170	27-29	2.5	1.10
			890	270	29-32	5.0	1.10
			1400	355	32-34	8.1	1.10
1.6	Short arc	18	180	145	15	1.5	1.10
			205	160	16	1.7	1.10
			230	170	18	1.9	1.10
1.6	Spray arc	25	380	235	25-26	2.9	1.10
			635	325	29-32	5.0	1.10
			890	400	34-37	7.0	1.10
			1145	460	36-38	9.1	1.10

FCAW

## WELDING PARAMETERS, OPTIMUM FILL PASSES IN SHIELDING GAS Ar + (>15-25)% CO<sub>2</sub>

Diameter (mm)	Welding positions				
	PA/1G	PB/2F	PC/2G	PF/3Gup	PE/4G
1.2	230-380A	230-380A	230-300A	130-170A	140-175A
	26-36V	26-36V	26-30V	15-17V	16-17V
1.4	240-385A	240-385A	240-340A	160-180A	175-185A
	26-36V	26-36V	26-31V	14-15V	15-16V
1.6	280-460A	280-460A	270-300A		
	28-36V	28-36V	28-30V		